

# TOGE TSM BC SB G

Adhesive screw anchor for fastening railings and contact protection for dynamic loads

**Steel, anti-corrosion coated, TOGE KORR**  
Corrosivity category C5 high



Item nr.	Designation	Depth of drill hole $h_o$	Embedment depth of anchor $h_{nom}$	Max. thickness of fixture $t_{fix}$	Packing Unit
204 142 200	TSM BC SB G 14x220 G M16 SW12	150 mm	140 mm	50mm	20

\* Production of special lengths possible on a project basis.

## Composite Mortar CF-T 300V

Chemical special mortar  
Vinylester styrene-free, suitable for concrete screws



### Product overview

Item nr.	Designation	Packing Unit
222 222 003	Cartridge CF-T 300V	1
222 223 001	Mixing nozzle for CF-T 300V	1
222 222 004	Squeezing pistol for CF-T 300V	1

### Processing Instructions

Temperature in ground	Processing time	Min. curing time in dry borehole	Min. curing time in wet borehole
$\geq -5^{\circ}\text{C}$	60 min	360 min	720 min
$\geq 0^{\circ}\text{C}$	60 min	180 min	360 min
$\geq 5^{\circ}\text{C}$	60 min	120 min	240 min
$\geq 10^{\circ}\text{C}$	45 min	80 min	160 min
$\geq 20^{\circ}\text{C}$	15 min	45 min	90 min
$\geq 30^{\circ}\text{C}$	5 min	25 min	50 min
$\geq 35^{\circ}\text{C}$	4 min	20 min	40 min